



Name: PolySorb Standard Colors Collection
Size Available: 4' x 8' & 4' x 10', Custom with MOQ
Thickness: 2.75" Standard
Core Density: 2.75" 3.5 PCF
NRC: 2.75" 1.10
SAA: 2.75" 1.12
Face Type: Ironed Smooth Face
FSI: Class A Flame Spread Index

NOAL Test 22-0940 Description of the test specimen

Specimen Size: 71.0 SF
Mount Method: Type A Mounting Method
Frame Construction: Placed Directly on The Test Surface


Air temp in the test room: 72.9°F
Air humidity in test room: 49.0%

Number of sound source positions: 2
Number of microphone positions
per sound source position: 3 Rotating Traverses
Type of noise used: Pink Random Noise
Type of mounting used: Type A Mounting
Airspace behind sample: 0"

Frequency f Hz	α - With Sample
100	0.69
125	0.37
160	0.70
200	0.83
250	0.90
315	1.04
400	1.07
500	1.20
630	1.32
800	1.24
1000	1.23
1250	1.20
1600	1.18
2000	1.16
2500	1.11
3150	1.13
4000	1.14
5000	1.10

Rating according to ASTM C423
Noise Reduction Coefficient = 1.10
Sound Absorption Average = 1.12

It is strongly recommended to use this single number rating in combination with the complete sound absorption coefficient curve. Sound absorption coefficients calculated at ASTM C423



going
green?
we can
help!



Name: PolySorb Standard Colors Collection
Size Available: 4' x 8' & 4' x 10', Custom with MOQ
Thickness: 2.75" Standard
Core Density: 2.75" 3.5 PCF
NRC: 2.75" 1.10
SAA: 2.75" 1.12
Face Type: Ironed Smooth Face
FSI: Class A Flame Spread Index

